









Photoluminescent Pigment

| Model | Size (D50)um | Afterglow intensity(mcd/m ²) | | | Glowing color (Night) | Appearance (Daytime) |
|--------|--------------|--|-------|-----------|--|---|
| | | 10 min | 60min | Glow time | | |
| HVB-5B | 65~85 | 700 | 120 | >12hour |  Blue-green |  Light-yellow |
| HVB-5C | 45~55 | 480 | 85 | | | |
| HVB-5D | 25~35 | 360 | 58 | | | |
| HVB-5E | 5~15 | 260 | 38 | | | |
| HVB-4B | 65~85 | 630 | 110 | 10 hour |  Blue-green |  Light-white |
| HVB-4C | 45~55 | 440 | 75 | | | |
| HVB-4D | 15~35 | 320 | 50 | | | |
| HVB-4E | 5~15 | 220 | 30 | | | |
| HVB-3C | 55~75 | 400 | 55 | | | |
| HVB-3D | 15~45 | 280 | 35 | | | |
| HVB-1C | 55~75 | 260 | 38 | | | |
| HVB-1D | 15~40 | 200 | 23 | | | |

Photoluminescent Pigment Coarse particles

| Model | Size (D50)mm | Afterglow intensity(mcd/m ²) | | | Glowing color (Night) | Appearance (Daytime) |
|---------|--------------|--|-------|-----------|--|---|
| | | 10 min | 60min | Glow time | | |
| HVB-5A | 0.5~2 | 880 | 145 | >12hour |  Blue-green |  Light-yellow |
| HVB-5BA | 0.15~0.3 | 790 | 140 | | | |
| HVB-4A | 0.5~2 | 770 | 130 | | | |
| HVB-4BA | 0.15~0.3 | 700 | 120 | | | |
| | | | | |  Blue-green |  Light-white |